

## UNITED “MEDIUM YELLOW” SILVER GRAIN # SY-2

United master alloy # **SY-2** has been formulated to be used in the manufacture of silver jewelry. Please note, this alloy is **NOT** recommended for making **STERLING SILVER JEWELRY**. This alloy has 25 % fine silver and is to be **directly** used for casting or for pouring into ingot for further sheet and wire making.

**CASTING TEMP:** **982° - 993° C / 1800° - 1820° F**

Do not overheat the metal. Boric acid flux may be used to keep the metal clean during the melting process. The metal should be mixed well with a stirring rod before pouring to assure a good mix

**QUENCHING TIME FOR FLASKS:** **20 to 30 minutes.**

**FLASK TEMPERATURE:** **650 C - 675 C** depending on size of flask and type of jewelry.

**POURING INGOT:** Metal should be poured into a preheated, vertical, lightly lubricated, 2 piece, L shaped mold with a 1/8 inch opening. A steady even pouring motion should be used slowing at the end of the pour to prevent shrinkage in the top of the ingot.

**INGOT QUENCHING:** The metal ingot should be removed from the mold and quenched immediately in pickle solution or water.

**FABRICATION:** The metal ingot should be cleaned of all adhering oxide or fluxes before rolling. The ingot should be rolled to a 10% - 15% reduction in thickness each time. Anneal the sheet after 50 % reduction. Clean the ingot after each anneal. Keep rolls, dies and metal clean to prevent defects in the finished stock.

**ANNEALING:** Annealing temperature **350° - 500° C / 662° - 932° F** for **20 minutes**. **Be careful handling the silver ingots when hot, as they can be fragile.** Air-cool the ingots for a minute before quenching in water.

**TECHNICAL ASSISTANCE** Always available... Call 1-800-999-3463 / 1-800-999-FINE  
E-mail / [techteam@unitedpmr.com](mailto:techteam@unitedpmr.com) Web-Site / [www.unitedpmr.com](http://www.unitedpmr.com)

---

2781 Townline Road, Alden, NY 14004, USA.  
Phone : (800) 999-3463; International Phone : +1-(716)-683-8334  
Fax : (800) 533-6657; International Fax : +1-(716)-683-5433  
E mail: [sales@unitedpmr.com](mailto:sales@unitedpmr.com); Website: [www.unitedpmr.com](http://www.unitedpmr.com)